

Technical data sheet

ROLA HARTIE MASCARE CERATA 90/400-40GR

Product Details

Product	HARTIE MASCARE CERATA	
Code	HKMGG40F900L400G50	
Colour	Brown	
Brand	Herzkraft	
Intrastat number	48043980	
Quality raw material	cellulose	
Grammage per ply	± 40	(g/m ²) PN-ISO 536
Nr. of Plies	1	-
Tensile strength	MD 3.53-4.32 / CD 1.57-1.76	[kN/m] PN-EN-ISO-1924-2
Tear resistance	MD 210-250 / CD 280-330	[mN] PN-EN-21974
Explosion resistance	170-210	[kPa] PN-EN-ISO-2758
Water absorbtion	25 max	Cobb60 [g/m ²] PN-ISO-535
Air permeability	150 max	Method Bendtsena, ml/min, ISO 5635-3
Wet tensile strength	18 min	%, ISO 3781
Humidity	6-9 max	[%] PN-ISO 287
Length	400	(mtr)
Width	90	(cm)
Sales unit (S.U.)	1	pieces/S.U.
Type of packaging	-	-
S.U. / pallet	65	pieces
Gross weight S.U.	14.4	kg
*Tolerance	± 2	%



Measurement conditions: relative humidity $50 \pm 2\%$; temperature $23 \pm 1^\circ\text{C}$ (PN-EN 20187)

The minimum values are guaranteed parameters.

Valtec 

KK
HERZKRAFT